

Product code: 10130DSC13X35
Product name: GORI 35 DECKING STAIN
Recommended for: Outdoor wooden decks

1 Product description

- 1.1 Product type: Translucent, water based, alkyd modified wood protection.
- 1.2 Manufacturer: PPG Coatings Danmark A/S - Gladsaxevej 300 - 2860 Søborg - DK
Phone: +45 39 57 93 00 - www.gori.com
- 1.3 Where to use: On all outdoor wooden decks and wood species.
- 1.4 Special qualities: Alkyd modified wood protection. Enhances the structure of the wood. Gives the wood a decorative and weather and UV-resistant surface. Easy to apply. Prevents surface attacks from blue stain and mould.
- 1.6 Form supplied: Ready to use

2 Composition

- 2.1 Solvents: Water.
- 2.2 VOC content: EU Limit value for this product Cat. A/E: 130 g/l (2010). This product contains max. 22 g/l VOC.
- 2.3 Pigments: Organic and inorganic pigments.
- 2.4 Active ingredients: 0.3% iodo-2-propynyl butylcarbamate.

3 Technical data

- 3.1 Specific gravity: ca. 1,01-1,1 g/ml.
- 3.2 Viscosity: 12 sec. (DIN cup 4 mm).
- 3.3 Solid content: ca. 17 w/w% / 16,1 v/v%.
- 3.4 Flash point: > 100°C (Pensky Martens)
- 3.5 Coverage: 12-16 m²/l depending on the substrate.
- 3.6 Drying time: Dust dry: app. 2 h. Recoat: app. 4-8 h. Walkable: app. 4-6 h. depending on temperature. Avoid heavy traffic the first few days after application. Complete drying: app. 3-4 weeks (at 23°C and standard humidity 60%).
- 3.7 Odour: Weak.



- 3.8 Thinning: Do not thin.
- 3.9 Storage: Store and transport in a cool, dry, frostfree environment without direct sunlight.
- 3.10 Shelf life: 3 years in unopened containers.

4 Surface and preparation

- 4.1 In general: Stir the product well before use. Dark nuances may contain surplus pigment, which may rub off. You can mix clear with pigmented 1:1, so the wood will not turn darker. This is especially recommended for maintenance coats.
- 4.2 Surface: The surface must be clean, dry and solid. At the time of treatment, the humidity should be max. 15 ± 3%.

5 Treatment

- 5.1 Application method: Apply by brush. Do not apply in direct sunlight. Temperature must be above 5°C and the relative humidity below 80%.
- 5.2 Pre-treatment: Remove any loose materials and dust. Clean with a suitable detergent (e.g. GORI Wood Cleaner), so mould and dust is removed. Deteriorated wood must be sanded down to sound wood.
- 5.3 Treatment: 1-2 coats GORI 35. Make sure not to apply too thick a layer in each coat.
- 5.4 Maintenance: 1-2 coats GORI 35. Treated wood should be inspected regularly and repaired if and when necessary.
- 5.5 Cleaning of tools: Soap and water.

6 Safety precautions

- 6.1 In general: Common safety rules for work with paints must be observed. Further information is available from our Material Safety Data Sheet.

7 Disposal

- 7.1 Disposal: Do not empty into drains or into the environment. Product waste must not be poured into the sewers, water reserves or soil.

The purpose of this Data Sheet is to inform our clients about the product's properties and characteristics. This information is based on tests made under conditions of use complying with effective standards. Our recommendations are given merely as an indication and do not replace specific recommendations related to the type and status of the work and timber to be treated. Before applying the product, clients should check for any updates of the Technical Data Sheet, and should bear in mind the new information provided, if any. This Technical Data Sheet replaces all previous versions.